

Klübersynth BQP 72-82

Rolling bearing grease for long-term lubrication



Benefits for your application

- **Extended component lifetime**
 - smooth running, especially in small rolling bearings ensures protection against premature material fatigue
 - above-average corrosion protection avoids corrosion damage
 - improved vibration resistance owing to optimised wear protection
- **Based on modern raw materials according to Bosch standard N 2580 (2008)**

Description

Klübersynth BQP 72-82 is designed for small rolling bearings in which material fatigue due to vibration in combination with pressure and temperature can occur. It is based on ester oil and polyurea thickener and made according to a special manufacturing procedure, facilitating smoother running of rolling bearings. With its above-average corrosion protection properties, it also extends the lifetime of rolling bearings.

to different system configurations and application conditions the pumpability of the product has to be confirmed with the system manufacturer for each individual application. We will be pleased to provide assistance in this matter.

Ideally, the friction point should be cleaned and dried prior to lubrication. If a preservative has been applied prior to greasing, we recommend checking compatibility with the lubricant.

Application

Klübersynth BQP 72-82 is preferably used for highly-loaded generator bearings, fan bearings and bearings in driving and electric motors, e.g. in cars.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Application notes

Klübersynth BQP 72-82 can be applied by means of brush, spatula, and automatic dosing units for small quantities or conventional dosing systems. The product is normally suitable for central lubricating systems. Please note, however, that due

Pack sizes

Product data	Klübersynth BQP 72-82
Article number	094116
Chemical composition, thickener	polyurea
Chemical composition, type of oil	ester oil
Lower service temperature	-40 °C / -40 °F
Upper service temperature	180 °C / 356 °F
Colour space	beige
Density at 20 °C	approx. 0.90 g/cm ³
Worked penetration, DIN ISO 2137, 25 °C, lower limit value	280 x 0.1 mm
Worked penetration, DIN ISO 2137, 25 °C, upper limit value	310 x 0.1 mm



Klübersynth BQP 72-82

Rolling bearing grease for long-term lubrication

Product data	Klübersynth BQP 72-82
Worked penetration, DIN ISO 2137, 25 °C, difference after 100,000 double strokes	<= 60 x 0.1 mm
Speed factor (n x dm)	approx. 1 000 000 mm/min
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 40 °C	approx. 80 mm ² /s
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 100 °C	approx. 11 mm ² /s
Corrosion inhibiting properties of lubricating greases, based on DIN 51802, SKF-EMCOR, test duration: 1 week, 5 % NaCl solution	<= 3 corrosion degree
Copper corrosion, DIN 51811, (lubricating grease), 24h/100°C	1 - 100 corrosion degree
Drop point, DIN ISO 2176, IP 396	>= 250 °C
Flow pressure of lubricating greases, DIN 51805, test temperature: -40 °C	<= 1 400 mbar
Noise test run: anerometer according KL-PN 035	<= 2/2
Oil separation, based on ASTM D 6184 [FTMS 791 C 321] after 30 h/150 °C	<= 3 % by weight
Water resistance, DIN 51807 pt. 01, 3 h/90 °C, rating	<= 1 - 90
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	12 months

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 80 years.

Klüber Lubrication München SE & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München SE & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München SE & Co. KG and if source is indicated and voucher copy is forwarded.